



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: C08G 18/48, B29C 33/60	A1	(11) International Publication Number: WO 00/55232 (43) International Publication Date: 21 September 2000 (21.09.2000)
(21) International Application Number: PCT/EP00/01514 (22) International Filing Date: 24 February 2000 (24.02.2000) (30) Priority Data: 99105419.8 17 March 1999 (17.03.1999) EP (60) Parent Application or Grant HUNTSMAN ICI CHEMICALS, LLC [/]; O. BLEYS, Gerhard, Jozef [/]; O. HUYGENS, Eric [/]; O. LEENSLAG, Jan-Willem [/]; O. MOUREAU, Herman, Eugene, Germain [/]; O. BLEYS, Gerhard, Jozef [/]; O. HUYGENS, Eric [/]; O. LEENSLAG, Jan-Willem [/]; O. MOUREAU, Herman, Eugene, Germain [/]; O. BAKEN, Philippus, Johannes, Leonardus, Henricus @ ; O.	Publish d	
(54) Title: PROCESS FOR PREPARING MOULDED POLYURETHANE MATERIAL (54) Titre: PROCEDE DE PREPARATION DE MATERIAU POLYURETHANNE MOULE		
(57) Abstract <p>Process for preparing a polyurethane material in a mould in which process the following steps are conducted: 1. an external mould release agent is applied onto at least those surfaces of the mould which will be in contact with the ingredients used for preparing the polyurethane material and/or the finished polyurethane material; 2. the ingredients to be used for preparing the polyurethane material are fed into the mould; 3. the ingredients are allowed to react and to form the polyurethane material; 4. the polyurethane material so formed is removed from the mould and 5. steps 2,3 and 4 are repeated at least 10 times without repeating step 1, wherein at least 25% by weight of the ingredients used to make the polyurethane material, excluding water in this calculation when used, consist of polyether polyol having a functionality of 2-6, an equivalent weight of 500-5000 and an oxyethylene content of at least 50% by weight.</p> (57) Abrégé <p>La présente invention concerne un procédé de préparation de polyuréthane dans un moule qui consiste 1) à appliquer un agent de démoulage externe au moins sur les surfaces du moule qui seront en contact avec les ingrédients utilisés dans la préparation du matériau polyuréthane et/ou avec le matériau polyuréthane terminé, 2) à placer dans le moule les ingrédients utilisés pour la préparation du matériau polyuréthane, 3) à laisser réagir les ingrédients et se former le matériau polyuréthane, 4) à enlever du moule le matériau polyuréthane formé, et 5) à répéter les étapes 2,3 et 4 au moins dix fois sans répéter l'étape 1. Dans ce procédé, au moins 25 % en poids des ingrédients utilisés dans la fabrication du matériau polyuréthane, en ne tenant pas compte de l'eau dans ce calcul lorsqu'elle est utilisée, consistent en polyéther de fonctionnalité 2-6, de poids équivalent 500-5000 et de teneur en oxyéthylène d'au moins 50 % en poids.</p>		

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08G 18/48, B29C 33/60	A1	(11) International Publication Number: WO 00/55232 (43) International Publication Date: 21 September 2000 (21.09.00)
(21) International Application Number: PCT/EP00/01514 (22) International Filing Date: 24 February 2000 (24.02.00) (30) Priority Data: 99105419.8 17 March 1999 (17.03.99) EP (71) Applicant (for all designated States except US): HUNTSMAN ICI CHEMICALS, LLC [US/US]; 500 Huntsman Way, Salt Lake City, UT 84108 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): BLEYS, Gerhard, Jozef [BE/BE]; Bremstraat 19, B-3001 Heverlee (BE). HUYGENS, Eric [BE/BE]; Pieter De Somerlaan 3, B-3001 Heverlee (BE). LEENSLAG, Jan-Willem [NL/BE]; Rechtstraat 10, B-3120 Tremelo (BE). MOUREAU, Herman, Eugene, Germain [BE/BE]; Potstraat 7, B-3300 Tienen (BE). (74) Agents: BAKEN, Philippus, Johannes, Leonardus, Henricus et al.; Huntsman ICI Europe Ltd., Huntsman Polyurethanes, Intellectual Property Dept., Everslaan 45, B-3075 Everberg (BE).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: PROCESS FOR PREPARING MOULDED POLYURETHANE MATERIAL (57) Abstract Process for preparing a polyurethane material in a mould in which process the following steps are conducted: 1. an external mould release agent is applied onto at least those surfaces of the mould which will be in contact with the ingredients used for preparing the polyurethane material and/or the finished polyurethane material; 2. the ingredients to be used for preparing the polyurethane material are fed into the mould; 3. the ingredients are allowed to react and to form the polyurethane material; 4. the polyurethane material so formed is removed from the mould and 5. steps 2,3 and 4 are repeated at least 10 times without repeating step 1, wherein at least 25% by weight of the ingredients used to make the polyurethane material, excluding water in this calculation when used, consist of polyether polyol having a functionality of 2-6, an equivalent weight of 500-5000 and an oxyethylene content of at least 50% by weight.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Description

5

10

15

20

25

30

35

40

45

50

55

5

Process for preparing moulded polyurethane material

10

The present invention is concerned with a process for preparing moulded polyurethane materials, in particular foams made from a considerable amount of a polyol having a relatively high oxyethylene (EO) content.

15

EP 547765 discloses the preparation of flexible foams using a considerable amount of a polyether polyol containing a considerable amount of oxyethylene groups. In general terms the making of mouldings has been disclosed.

10

20

WO 97/21750 discloses the preparation of moulded elastomers using the same type of polyols in high amount.

25

15

US 5700847 and US 5668191 disclose the preparation of moulded flexible foams as well.

30

20

35

None of these citations touches upon a problem encountered in making such moulded foams commercially. Commercially such foams are made using moulds which have been treated before use : the surfaces, which will be in contact with the ingredients used for preparing the polyurethane material and/or with the finished polyurethane material, are provided with one or more so-called external mould release agents. After having made 5 or 6 mouldings these surfaces need to be provided with an external mould release agent again. In most cases the application of this external mould release agent onto said surfaces is conducted manually; whether it is conducted manually or automatically, this repetitive application of external mould release agent increases the cycle time and the amount of external mould release agent used. Further it has been experienced in practice that the external mould release agent during the moulding process is concentrated at certain parts of the surface of the mould (so called 'build-up'), which requires thorough cleaning of the surface regularly.

40

25

45

30

50

55

5

10

EP 547760 discloses a process for making moulded elastomers; more than 100 mouldings could be done without applying external mould release agent. The reaction systems used comprise allophanate-modified polyisocyanate and a considerable amount of a polyether polyol having a relatively high oxypropylene content.

15

20

Many disclosures have been made in the past to improve demoulding by using an internal mould release agent; see e.g. EP 119471 and EP 173888 and the prior art discussed therein.

25

It would be advantageous to be able to make moulded flexible polyurethane foams without the need to apply external mould release agent as often as nowadays. Further it would be advantageous to reduce the total amount of external mould release agent used when making mouldings and to reduce the build-up.

30

Surprisingly, we have found that it is possible to reduce the number of times external mould release agent needs to be applied, the total amount of external mould release agent used in the moulding process and the build-up by using a substantial amount of a polyol having a substantial amount of oxyethylene groups in preparing the moulded material.

35

40

Therefore the present invention is concerned with a process for preparing a polyurethane material in a mould in which process the following steps are conducted :

45

1. an external mould release agent is applied onto at least those surfaces of the mould which will be in contact with the ingredients used for preparing the polyurethane material and/or the finished polyurethane material;
2. the ingredients to be used for preparing the polyurethane material are fed into the mould;

30

50

55

- 5
3. the ingredients are allowed to react and to form the polyurethane material;
4. the polyurethane material so formed is removed from the mould and
- 10 5. steps 2,3 and 4 are repeated at least 10 times without repeating step 1, wherein at least 25% by weight of the ingredients used to make the polyurethane
- 5 material, excluding water in this calculation if used, consist of polyether polyol having an average nominal functionality of 2-6, an average equivalent
- 15 weight of 500-5000 and an oxyethylene content of at least 50% by weight.

In the context of the present invention the following terms have the following

10 meaning :

- 20 1) isocyanate index or NCO index or index :
- the ratio of NCO-groups over isocyanate-reactive hydrogen atoms present in a formulation, given as a percentage :

25
$$\frac{[\text{NCO}] \times 100}{[\text{active hydrogen}]} \quad (\%).$$

15

30 In other words the NCO-index expresses the percentage of isocyanate actually used in a formulation with respect to the amount of isocyanate theoretically required for reacting with the amount of isocyanate-reactive hydrogen used in a

20 formulation.

35 It should be observed that the isocyanate index as used herein is considered from the point of view of the actual foaming process or other process in the mould involving the isocyanate ingredients and the isocyanate-reactive ingredients. Any

40 25 isocyanate groups consumed in a preliminary step to produce modified polyisocyanates (including such isocyanate-derivatives referred to in the art as prepolymers) or any active hydrogens consumed in a preliminary step (e.g. reacted with isocyanate to produce modified polyols or polyamines) are not taken

45 into account in the calculation of the isocyanate index. Only the free isocyanate

groups and the free isocyanate-reactive hydrogens (including those of the water) present at the actual reaction in the mould are taken into account.

- 2) The expression "isocyanate-reactive hydrogen atoms" as used herein for the purpose of calculating the isocyanate index refers to the total of active hydrogen atoms in hydroxyl and amine groups present in the reactive compositions; this means that for the purpose of calculating the isocyanate index at the actual foaming process one hydroxyl group is considered to comprise one reactive hydrogen, one primary amine group is considered to comprise one reactive hydrogen and one water molecule is considered to comprise two active hydrogens.
- 3) Reaction system : a combination of components wherein the polyisocyanates are kept in one or more containers separate from the isocyanate-reactive components.
- 4) The expression "polyurethane foam" as used herein refers to cellular products as obtained by reacting polyisocyanates with isocyanate-reactive hydrogen containing compounds, using foaming agents, and in particular includes cellular products obtained with water as reactive foaming agent (involving a reaction of water with isocyanate groups yielding urea linkages and carbon dioxide and producing polyurea-urethane foams) and with polyols, aminoalcohols and/or polyamines as isocyanate-reactive compounds.
- 5) The term "nominal hydroxyl functionality" is used herein to indicate the functionality (number of hydroxyl groups per molecule) of the polyol or polyol composition on the assumption that this is the functionality (number of active hydrogen atoms per molecule) of the initiator(s) used in

5
their preparation although in practice it will often be somewhat less
because of some terminal unsaturation.

10
6) The word "average" refers to number average unless indicated otherwise.

5
The polyurethane material made according to the process of the present invention
15 may be an elastomer, a microcellular elastomer, a thermoplastic polyurethane, an
integral skin semi-rigid foam, a flexible foam or a hydrophilic foam like those of
the type disclosed in EP 707607 and EP 793681. The materials made e.g. may be
20 used as body parts in automobiles like steering wheels, arm-rests and head-rests,
as shoe soles, as the foam material in automotive seating or furniture, in medical
and hygienic applications like wound dressing, tampons and diapers, and in
leisure products like dolls. The materials obtained have comparable physical
25 properties irrespective of whether the material is obtained after steps 2,3 and 4
15 have been conducted once, 10 times, 25 times, 40 times or even more.

The moulding process may be conducted in an open mould and in a closed mould;
preferably the reaction takes place in a closed mould. When the moulding process
30 is conducted in a closed mould, the mould may be closed after step 2, and opened
after step 3 or the mould may be closed after step 1 and opened after step 3; in the
20 latter case the ingredients for making the polyurethane material are fed into the
mould via appropriate inlets. The moulding may be conducted by processes
35 known in the art like cast moulding and reaction injection moulding (RIM,
including so-called structural RIM).

As said, step 2 - 4 are repeated at least 10 times without repeating step 1;
40 preferably this is at least 15 times and most preferably at least 25 times. Although,
it would be desirable that steps 2 - 4 could be repeated as many times as possible
without repeating step 1, practice has shown that it may be desirable to repeat step
45 1, after steps 2 - 4 have been repeated a considerable number of times without
repeating step 1. In general it can be said that step 1 is to be repeated when a
30 substantial increase of the force needed to remove a moulded part is observed,

5 compared to the force needed to remove the first moulded part, to such an extent
that it is to be expected that the next demoulding can not be made without
10 damaging the part. Those involved in demoulding on commercial production
lines will be able easily to determine if and when step 1 is to be repeated.

5 Although not yet needed because of deteriorating demoulding performance, it
might nevertheless be desirable to repeat step 1 after a certain time period, in
15 order to have a consistent production process. In that context it might be desirable
to repeat step 1 between two shifts (of e.g. 8 hours), after 24 hours or after a week
depending on the complexity of the mould. It is to be noted that an usual cycle
20 time generally is between 0.5 and 20 minutes and often between 1 and 10 minutes.
Practice has shown that for flexible foams such repetition of step 1 is not
necessary before 50 mouldings have been made.

25 The ingredients used to make the polyurethane material are known in the art.

15 As said at least 25% by weight of the ingredients, excluding the amount of water
if used, consist of a polyether polyol having a number average nominal
30 functionality of 2-6, an oxyethylene group content of at least 50% by weight and
preferably of 60-90% by weight (calculated on the weight of the polyether polyol)
20 and a number average equivalent weight of 500-5000. The polyether polyol may
35 contain, together with the oxyethylene groups, other oxyalkylene groups, like
oxypropylene and oxybutylene groups.

40 When the polyether polyol contains other oxyalkylene groups the polyether polyol
25 may be in the form of a block copolymer, a random copolymer or a combination
of block- and random copolymer. Most preferably random copolymers are used.
Polyoxyethylene polyols, like polyoxyethylene glycols having a molecular weight
45 of 1000-2000, may be used as well.

The polyether polyol most preferably is a polyoxyethylene polyoxypropylene
30 polyol having a number average nominal functionality of 2-4, a number average

5 equivalent weight of 750-2500 and an oxyethylene content of 60-90% by weight;
most preferably the polyoxyethylene polyoxypropylene polyol is a random polyol:
10 such polyols are commercially available, examples being DaltocelTM 442 from
Huntsman Polyurethanes (Daltocel is a trademark of Huntsman ICI Chemicals
5 LLC), ArcolTM 2580 from Lyondell and CP1421 from DOW. Mixtures of these
polyols having a high oxyethylene content may be used as well.

15 The amount of the above polyol calculated on all ingredients used, excluding the
amount of water if used, preferably is 50-90% by weight and more preferably 60-
20 85% by weight.

25 The other ingredients used in making the polyurethane materials are known as
such and are polyisocyanates and, in case foamed polyurethane materials are
made, blowing agents. Further the following ingredients may be used as optional
15 ingredients: further isocyanate-reactive compounds like polyether polyols of a
type different from those described above e.g. polyoxypropylene polyols
optionally having less than 50% and preferably less than 25% by weight of
30 oxyethylene groups at the end of the polymer chains (so called EO-tipped
polyols), polyester polyols, polyether polyamines, these compounds having a
20 number average nominal functionality of 2-6, preferably of 2-3 and a number
average equivalent weight of 500-5000, preferably of 1000-3000, and like chain
35 extenders and cross-linkers which are isocyanate-reactive compounds having an
equivalent weight below 500 and a functionality of 2 and 3-8 respectively.

40 Examples of such chain-extenders and cross-linkers are ethylene glycol, propane
25 diol, 2-methyl-propane-1,3 diol, butanediol, pentane diol, hexane diol, diethylene
glycol, propylene glycol, dipropylene glycol, polyoxyethylene diols and triols
having an equivalent weight below 500, glycerol, trimethylolpropane,
45 pentaerythritol, sucrose, sorbitol, mono-, di- and triethanolamine,
ethylenediamine, toluenediamine, diethyltoluene diamine and polyether diamines
30 and triamines having an equivalent weight below 500.

5

10

15

20

25

30

35

40

45

50

55

Still further the following optional ingredients may be used: catalysts enhancing the formation of urethane bonds like metal catalysts like tin octoate and dibutyltin dilaurate, tertiary amine catalysts like triethylenediamine and imidazoles like dimethylimidazole and other catalysts like maleate esters and acetate esters; surfactants; fire retardants; smoke suppressants; UV-stabilizers; colorants; microbial inhibitors; fillers; internal mould release agents (such agents may be used to further enhance the release of the materials made but are not essential as shown in the Examples).

10 The polyols used in making the polyurethane materials and in particular the flexible foams may comprise dispersions or solutions of addition or condensation polymers.

Such modified polyols, often referred to as "polymer polyols", have been fully described in the prior art and include products obtained by the in situ polymerisation of one or more vinyl monomers, for example styrene and/or acrylonitrile, in the above polyether polyols, or by the in situ reaction between a polyisocyanate and an amino- and/or hydroxy-functional compound, such as triethanolamine, in the above polyol.

20 The amount of dispersed polymer may range from 0.1 to 10% by weight on all ingredients. Particle sizes of the dispersed polymer of less than 50 microns are preferred.

25 During the last years several methods have been described to prepare polyether polyols having a low level of unsaturation. These developments have made it possible to use polyether polyols at the higher end of the molecular weight range since such polyols can now be prepared with an acceptably low level of unsaturation. According to the present invention polyols having a low level of unsaturation may be used as well. In particular such high molecular weight

polyols having a low level of unsaturation may be used for preparing flexible foams having a high ball rebound and resilience.

If a foamed polyurethane is made a blowing agent is used. Blowing agents known in the art may be used like hydrocarbons, so called CFC's and HCFC's, N₂, CO₂ and water. Most preferably water is used as the blowing agent, optionally together with CO₂. The amount of blowing agent will depend on the desired density. Those skilled in the art will be able to determine the amount depending on the desired density and the blowing agent used. When water is used the amount will be up to 4 times the weight of all other ingredients used. For a flexible foam used in car seating and furniture the amount of water will be between 0.8-5% by weight; for a microcellular elastomer and an integral skin semi-rigid foam in general up to 0.8% by weight will be used and for hydrophilic foams more than 5% by weight preferably 20-300% by weight will be used; all amounts calculated on the amount of all other ingredients used.

Polyisocyanates used for preparing the polyurethane materials may be selected from aliphatic, cycloaliphatic and araliphatic polyisocyanates, especially diisocyanates, like hexamethylene diisocyanate, isophorone diisocyanate, cyclohexane-1,4-diisocyanate, 4,4-dicyclohexylmethane diisocyanate and m- and p- tetramethylxylylene diisocyanate, and in particular aromatic polyisocyanates like toluene diisocyanates (TDI), phenylene diisocyanates, naphthalene diisocyanates and most preferably methylene diphenylene diisocyanates (MDI) and its homologues having an isocyanate functionality of more than two, like crude MDI and polymeric MDI.

Preferred polyisocyanates are methylene diphenylene diisocyanates selected from pure 4,4'-MDI, isomeric mixtures of 4,4'-MDI, 2,4'-MDI and less than 10% by weight of 2,2'-MDI, and modified variants of these diisocyanates containing carbodiimide, uretonimine, and/or urethane groups, like uretonimine and/or carbodiimide modified MDI having an NCO content of at least 20% by weight and urethane modified MDI obtained by reacting excess MDI and a low molecular

weight polyol (molecular weight of up to 1000) and having an NCO content of at least 20% by weight.

Mixtures of the isocyanates mentioned above may be used if desired.

The polyisocyanate may, if desired, contain dispersed urea particles and/or urethane particles prepared in a conventional way, e.g. by adding a minor amount of an isophorone diamine to the polyisocyanate.

The most preferred polyisocyanate is a polyisocyanate containing at least 65%, preferably at least 80% and more preferably at least 95% by weight of 4,4'-diphenyl methane diisocyanate or a variant thereof. It may consist essentially of

pure 4,4'-diphenyl methane diisocyanate or mixtures of that diisocyanate with one or more other organic polyisocyanates, especially other diphenyl methane diisocyanate isomers, for example the 2,4'-isomer optionally in conjunction with the 2,2'-isomer. The most preferred polyisocyanate may also be an MDI variant derived from a polyisocyanate composition containing at least 65% by weight of 4,4'-diphenylmethane diisocyanate. MDI variants are well known in the art and, for use in accordance with the invention, particularly include liquid (at 25°C) products obtained by introducing uretonimine and/or carbodiimide groups into said polyisocyanates, such a carbodiimide and/or uretonimine modified polyisocyanate preferably having an NCO value of at least 20% by weight, and/or by reacting such a polyisocyanate with one or more polyols having a hydroxyl functionality of 2-6 and a molecular weight of 62-1000 so as to obtain a modified polyisocyanate, preferably having an NCO value of at least 20% by weight. Up to 25% by weight of another polyisocyanate may be used together with this most preferred polyisocyanate; preferred other polyisocyanates are polymeric MDI and toluene diisocyanate.

The reaction to prepare the polyurethane materials, except the hydrophilic foams, may be conducted at an NCO-index of 40-150 and preferably of 70-110. For the hydrophilic foams the NCO index may vary much wider in view of the large amount of water used.

5 The polyurethane materials may be prepared according to the one-shot method and the prepolymer method. According to the one-shot method the
10 polyisocyanate, the polyether polyol having at least 50% by weight of oxyethylene groups and the other, optional ingredients are fed into the mould and
5 reaction is allowed to take place in the mould; if desired the polyether polyol and the other, optional ingredients are premixed.

15 According to the prepolymer method part or all of the isocyanate-reactive compounds, except water if used, are pre-reacted with an excessive amount of polyisocyanate to prepare a urethane-containing, isocyanate-terminated
10 prepolymer; the prepolymer so formed is reacted with the remaining isocyanate-reactive compounds and/or the water. An especially preferred embodiment of the present invention is the use of an isocyanate-terminated, urethane-containing
20 prepolymer having an NCO value of 3-30 and preferably of 3-15% by weight in the process of the present invention, in particular when flexible polyurethane
25 foams are made by using this prepolymer together with water. The prepolymer is an isocyanate-terminated, urethane-containing prepolymer made by reacting an excessive amount of a polyisocyanate containing at least 65% by weight of 4,4'-
30 diphenylmethane diisocyanate or a variant thereof with a polyoxyethylene polyoxypropylene polyol having a number average nominal functionality of 2-4, a number average equivalent weight of 750-2500 and an oxyethylene content of 60-
20 90% by weight.

35 The preparation of such prepolymers and the prepolymers are known in the art: see e.g. EP 547765.

40 25 For the avoidance of doubt, in calculating the amount of polyether polyol having an oxyethylene content of at least 50% by weight in the polyurethane material, the amount of such polyol in a prepolymer is to be taken into account as well.

45 When such a prepolymer is used the flexible foam is prepared by reacting the prepolymer with water and optionally with further polyether polyol having an
30 oxyethylene group content of at least 50% by weight and optionally with further

50

55

5

10

isocyanate reactive ingredients and optionally in the presence of the described optional ingredients. The amount of water used is 0.8-5% by weight calculated on all other ingredients used. A small amount, up to 25% by weight calculated on the weight of the prepolymer, of another polyisocyanate may be used to prepare the flexible foams; preferably such other polyisocyanates are polymeric MDI and/or toluene diisocyanate.

15

The flexible foams may have apparent overall densities varying from 20 to 150 kg/m³ (ISO 845).

20

10 The process may be conducted in any type of mould known in the art. Examples of such moulds are the moulds commercially used for making polyurethane furniture parts, automotive seating and automotive parts, like steering wheels, arm-rests and head-rests.

25

The material of the mould may be selected from those known in the art like metal, c.g. aluminium, and epoxy resin.

30

Step 1 of the process according to the invention may be conducted in any way known in the art. Applying an external mould release agent on the surfaces of a mould, which surfaces will be in contact with the ingredients used for making the material and/or with the material includes any way of applying such an agent to the surfaces, like rubbing, brushing, spraying and combinations thereof and applying any agent or agents intended to facilitate the later demoulding. One or more external mould release agents may be used or mixtures of external release agents.

35

40

The external mould release agents may be applied as such or as a solution, emulsion or dispersion in a liquid.

45

The external mould release agents, applied in step 1, may be applied in one or more stages. Any external mould release agent known in the art may be applied; examples of suitable external mould release agents are Klüberpur 41-0039 and 41-0061 (both from Klüber Chemie), Desmotrol D-10RT from Productos Concentrol

50

55

5 S.A., Acmosil 180 STBH from Fuller and Johnson Cire 103 from Johnson and Johnson.

10 Further it was surprisingly found that flexible polyurethane foams, prepared as
5 described hereinbefore and having a relatively high density, show an
extraordinary combination of properties. Therefore the present invention is
15 further concerned with a moulded flexible polyurethane foam having an apparent
overall density of 55-150 and preferably of 55-100 kg/m³, a vibration
transmissibility at resonance frequency of 1.5-3.2, a resonance frequency of at
20 most 3.5 Hz and a hardness at an indentation load deflection (ILD) of 25% of 15-
25 kg and comprising oxyethylene and oxypropylene groups in a weight ratio of
1:1 to 8:1 and oxyethylene groups in an amount of 25-80% by weight, calculated
on the weight of the foam.

25 Preferably such foams have a resonance frequency between 2.6 and 3.4 Hz, a
15 vibration transmissibility at 6 Hz of less than 1, preferably of 0.3-0.9, a resilience
of at least 50% and preferably of 55-80% and an amount of oxyethylene groups of
35-75% by weight.

30 The density, vibration transmissibility at resonance frequency and at 6 Hz, the
resonance frequency, hardness and resilience are measured as follows :

20 density, kg/m³ : ISO 845

35 vibration transmissibility at resonance frequency : JASO B407-82

vibration transmissibility at 6 Hz : JASO B407-82

resonance frequency : JASO B407-82

hardness, ILD of 25%, kg : ISO 2439:1977 (E)

40 25 resilience, % : ISO 8307:1990 (E)

This JASO test B 407-82 is conducted at 23°C and a relative humidity of 50%.
using a sample of 450x450x1000 mm and an indenter of the Tekken type which
45 indenter has a weight of 50 kg.

50 These foams preferably are prepared by using the most preferred polyisocyanates
30 and polyols mentioned hereinbefore.

5 Foams having a resonance frequency below 3.5 Hz have been disclosed in EP 394487; however such foams contain a high amount of oxypropylene groups.

10 The present invention is illustrated by the following examples.

5

Example 1

15 A moulded flexible polyurethane foam was made in a metal mould (internal dimensions 30x30x7 cm). The parts of the mould which will be in contact with the ingredients for making the foam and/or with the foam were first rubbed with
20 Johnson Circ 103 (a wax obtainable from Johnson and Johnson) and then sprayed with Klüberpur 41-0039 (an external mould release agent obtainable from Klüber Chemie).

25 The following ingredients were used for preparing the foam

- 15 - polyol 1 : a random polyoxyethylene polyoxypropylene polyol having a nominal functionality of 3, an oxyethylene content of about 77 % by weight and a molecular weight of about 4000;
30 - SuprasecTM MPR from Huntsman Polyurethanes, Suprasec is a trademark of Huntsman ICI Chemicals LLC.
20 - Niox A1, an amine catalyst from OSI; and
35 - water.

40 First a prepolymer was made by reacting 70 parts by weight of polyol 1 and 30 pbw of SuprasecTM MPR containing 40 ppm of thionylchloride. The prepolymer
25 had an NCO value of 7.8% by weight.

86.7 pbw of this prepolymer and a mixture consisting of 11.8 pbw of polyol 1, 0.15 pbw of Niox A1 and 1.38 pbw of water were hand mixed in a cup (3000 rpm for 7 seconds) and this mixture was poured into the mould; total amount of the
45 mixture was 495 grams. The mould was closed and the ingredients were allowed

50

55

5 to react (mould temperature 45°C). 6 minutes after closing the mould, the mould was opened and the foam was removed.

10 Immediately after removal of the foam and without any treatment of the mould, the same amount of ingredients (prepolymer, Polyol 1, Niox A1 and water) were
5 poured into the mould as above, the mould was closed, the ingredients were allowed to react and the foam was demoulded after the same moulding time; this
15 procedure was repeated 50 times. Then the experiment was voluntarily stopped. In total 52 moulded flexible polyurethane foams were made; all foams could be demoulded easily and without any damage to the foam. The foams obtained had
20 an apparent overall density of about 75 kg/m³ (ISO 845).

Example 2

25 Example 1 was repeated with the following ingredients with the proviso that the mould was used without treatment with Johnson Cire 103 and Klüberpur 41-0039;
15 the mould was used as it was after the 52 mouldings in example 1 were made.

Ingredients :

- 30 - SuprasecTM 2010 ex Huntsman Polyurethanes
- polyol 1
- 2-methyl-propane-1,3-diol (MP)
- 20 - Dabco-DC-2 (catalyst from Air Products)

35 62.4 pbw of polyol 1. 6.9 pbw of MP and 0.14 pbw of DC2 were blended.

This blend was mixed as in example 1 with 30.5 pbw of SuprasecTM 2010.

40 Moulded materials were made as in example 1, with the exception that the mould was not closed. 16 mouldings were made without using any external mould
25 release agent. All mouldings could be removed easily and without damage.

Example 3

45 Foams made in a similar way as in example 1 had the following physical properties :

30 Apparent overall density : 71 kg/m³ (ISO 845)

5

10

15

20

25

30

35

40

45

50

55

5

Vibration transmissibility at resonance frequency : 1.99 (JASO B407-82)

Resonance frequency : 3.08 Hz (JASO B407-82)

10

Hardness (ILD of 25%) : 20 kg (ISO 2439:1977 (E))

Resilience : 64% (ISO 8307:1990 (E))

5 Compression set at 50%, dry : 3% (ISO 1856)

Compression set at 50%, humid : -1.7% (TSM 7100)

15

Vibration transmissibility at 6 Hz : 0.73 (JASO B407-82)

20

25

30

35

40

45

50

55

Claims

5

10

15

20

25

30

35

40

45

50

55

5

Claims

10

1. Process for preparing a polyurethane material in a mould in which process the following steps are conducted :

5

15

1. an external mould release agent is applied onto at least those surfaces of the mould which will be in contact with the ingredients used for preparing the polyurethane material and/or the finished polyurethane material;

20

10

2. the ingredients to be used for preparing the polyurethane material are fed into the mould;

3. the ingredients are allowed to react and to form the polyurethane material;

4. the polyurethane material so formed is removed from the mould and

25

15

5. steps 2,3 and 4 are repeated at least 10 times without repeating step 1, wherein at least 25% by weight of the ingredients used to make the polyurethane material, excluding water in this calculation if used, consist of polyether polyol having an average nominal functionality of 2-6, an average equivalent weight of 500-5000 and an oxyethylene content of at least 50% by weight.

30

20

2. Process according to claim 1 wherein steps 2, 3 and 4 are repeated at least 15 times without repeating step 1.

35

3. Process according to claim 1 wherein steps 2, 3 and 4 are repeated at least 25 times without repeating step 1.

40

25

4. Process according to claims 1-3 wherein a flexible polyurethane foam is prepared comprising reacting a polyisocyanate, the polyether polyol and water.

45

50

55

5

10

15

20

25

5. Process according to claims 1-3 wherein the ingredients comprise : 1) an isocyanate-terminated, urethane-containing prepolymer made by reacting an excessive amount of a polyisocyanate containing at least 65% by weight of 4,4'-diphenylmethane diisocyanate or a variant thereof with a polyoxyethylene polyoxypropylene polyol having a number average nominal functionality of 2-4, a number average equivalent weight of 750-2500 and an oxyethylene content of 60-90% by weight, the prepolymer having an NCO value of 3-15% by weight; and 2) water.

10 6. Process according to claims 4-5 wherein the amount of water is 0.8-5% by weight calculated on all ingredients used.

15 7. Process according to claims 4-6, wherein the amount of the polyether polyol having at least 50% by weight of oxyethylene groups is at least 50% by weight calculated on all ingredients used.

30 8. Process according to claims 4-7 wherein the reaction is conducted at an NCO index of 40-150.

20 9. Process according to claim 8 wherein the index is 70-110.

35 10. Process according to claims 1-9 wherein step 1 is repeated after one week.

40 11. Process according to claims 1-9 wherein step 1 is repeated after 24 hours.

25

12. Process according to claims 1-9 wherein step 1 is repeated after 8 hours.

45

50

55

5

10

13. Moulded flexible polyurethane foam having an apparent overall density of 55-150 kg/m³, a vibration transmissibility at resonance frequency of 1.5-3.2, a resonance frequency of at most 3.5 Hz, and a hardness (ILD of 25%) of 15-25 kg and comprising oxyethylene and oxypropylene groups in a weight ratio of 1:1 to 8:1 and oxyethylene groups in an amount of 25-80% by weight calculated on the weight of the foam.

15

20

14. Foam according to claim 13 wherein the density is 55-100 kg/m³, the resonance frequency is between 2.6 and 3.4 Hz, the vibration transmissibility at 6 Hz is less than 1, the resilience is at least 50% and the amount of oxyethylene groups is 35-75% by weight.

25

15. Foam according to claims 13-14 wherein the vibration transmissibility at 6 Hz is 0.3-0.9 and the resilience is 55-80%.

15

30

35

40

45

50

55

INTERNATIONAL SEARCH REPORT

Inter. Appl. No.
PCT/EP 00/01514

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C08G18/48 B29C33/60		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C08G B29C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) WPI Data, EPO-Internal, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 416 399 A (DOW CHEMICAL) 13 March 1991 (1991-03-13) page 2, line 23 -page 7, line 19 page 8, line 21 - line 32; example 15	1-3
A	EP 0 180 749 A (BAYER) 14 May 1986 (1986-05-14) page 2, line 14 -page 6, line 25 page 16, line 10 -page 17, line 24; example 13	1-3
A	WO 98 00450 A (IMPERIAL CHEMICAL INDUSTRIES) 8 January 1998 (1998-01-08) page 1, line 19 -page 3, line 14; claims 1,4-13	1
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "B" document member of the same patent family		
Date of the actual completion of the international search 7 August 2000		Date of mailing of the international search report 14/08/2000
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3018		Authorized officer Bourgonje, A

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/EP 00/01514

C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 97 21750 A (IMPERIAL CHEMICAL INDUSTRIES) 19 June 1997 (1997-06-19) cited in the application page 2, line 11 -page 3, line 36; claim 11	1
A	EP 0 547 760 A (IMPERIAL CHEMICAL INDUSTRIES) 23 June 1993 (1993-06-23) cited in the application page 2, line 15 -page 3, line 27; claims 1-3; examples	1

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No.

PCT/EP 00/01514

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 416399 A	13-03-1991	US 5070110 A	03-12-1991
		AU 6135290 A	28-02-1991
		BR 9004287 A	03-09-1991
		CA 2023979 A	26-02-1991
		JP 3106922 A	07-05-1991
		US 5162382 A	10-11-1992
EP 180749 A	14-05-1986	DE 3436163 A	10-04-1986
		AU 571112 B	31-03-1988
		AU 4749885 A	10-04-1986
		BR 8504862 A	22-07-1986
		CA 1252945 A	18-04-1989
		DE 3563214 D	14-07-1988
		ES 547490 D	16-07-1986
		ES 8609392 A	16-12-1986
		JP 1029493 B	12-06-1989
		JP 61091216 A	09-05-1986
		US 4609682 A	02-09-1986
WO 9800450 A	08-01-1998	AU 3171297 A	21-01-1998
		BR 9709988 A	10-08-1999
		CA 2258677 A	08-01-1998
		EP 0912623 A	06-05-1999
		PL 330920 A	07-06-1999
		US 5968993 A	19-10-1999
WO 9721750 A	19-06-1997	AU 718820 B	20-04-2000
		AU 7625896 A	03-07-1997
		BR 9611977 A	17-02-1999
		CA 2239482 A	19-06-1997
		CN 1208423 A	17-02-1999
		EP 0865458 A	23-09-1998
		JP 2000501756 T	15-02-2000
		PL 327198 A	23-11-1998
EP 547760 A	23-06-1993	DE 69216213 D	06-02-1997
		DE 69216213 T	15-05-1997
		ES 2095416 T	16-02-1997
		JP 5239170 A	17-09-1993
		US 5260346 A	09-11-1993

